



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B41N	A2	(11) International Publication Number: WO 00/37261 (43) International Publication Date: 29 June 2000 (29.06.00)
(21) International Application Number: PCT/GB99/04238 (22) International Filing Date: 14 December 1999 (14.12.99) (30) Priority Data: 9828154.6 22 December 1998 (22.12.98) GB (71) Applicant (for all designated States except US): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): NEWINGTON, Ian, Martin [GB/GB]; 11 Ashtree Walk, Hazlemere, High Wycombe, Bucks HP15 7TG (GB). WEAR, Trevor, John [GB/GB]; 22 Balmoral Road, South Harrow, Middlesex HA2 8TD (GB). (74) Agent: NUNNEY, R., F., A.; Kodak Limited, Headstone Drive, Harrow, Middlesex HA1 4TY (GB).		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: PRINTING PLATES AND A METHOD FOR THEIR PREPARATION (57) Abstract <p>A method for the preparation of a lithographic printing plate comprises forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both hydrophilic and hydrophobic groups. The number of repeating units in the oligomer may be from 2 to 10 and the number of hydrophilic groups in the oligomer may also be from 2 to 10. Preferably the molecular weight of the oligomer is from about 500 to about 5000.</p> <div style="text-align: center;"> </div>		



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B41N	A2	(11) International Publication Number: WO 00/37261 (43) International Publication Date: 29 June 2000 (29.06.00)
(21) International Application Number: PCT/GB99/04238 (22) International Filing Date: 14 December 1999 (14.12.99) (30) Priority Data: 9828154.6 22 December 1998 (22.12.98) GB (71) Applicant (for all designated States except US): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): NEWINGTON, Ian, Martin [GB/GB]; 11 Ashtree Walk, Hazlemere, High Wycombe, Bucks HP15 7TG (GB). WEAR, Trevor, John [GB/GB]; 22 Balmoral Road, South Harrow, Middlesex HA2 8TD (GB). (74) Agent: NUNNEY, R., F., A.; Kodak Limited, Headstone Drive, Harrow, Middlesex HA1 4TY (GB).		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: PRINTING PLATES AND A METHOD FOR THEIR PREPARATION		
(57) Abstract <p>A method for the preparation of a lithographic printing plate comprises forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both hydrophilic and hydrophobic groups. The number of repeating units in the oligomer may be from 2 to 10 and the number of hydrophilic groups in the oligomer may also be from 2 to 10. Preferably the molecular weight of the oligomer is from about 500 to about 5000.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PRINTING PLATES AND A METHOD FOR THEIR PREPARATION.**Field of the Invention**

This invention relates to novel printing plates, to a
5 method for their preparation and to a lithographic
printing process employing the plates.

Background of the Invention

Printing plates suitable for offset lithographic
printing are known which comprise a support having
10 non-image areas which are hydrophilic and image areas
which are hydrophobic and ink-receptive.

The art of lithographic printing is based upon the
immiscibility of oil and water, wherein the oily
material or ink is preferentially retained by the
15 image area and water or fountain solution is
preferentially retained by the non-image area. When a
suitably prepared surface is moistened with water and
an ink is then applied the background or non-image
area retains the water and repels the ink while the
20 image area accepts the ink and repels the water. The
ink on the image area is then transferred to the
surface of a material upon which the image is to be
reproduced, such as paper, cloth and the like.

Commonly the ink is transferred to an intermediate
25 material called the blanket which in turn transfers
the ink to the surface of the material upon which the
image is to be reproduced.

Ink-jetting is the non-impact method for producing
images by the deposition of ink droplets on a
30 substrate in response to digital signals.

JP-A-53015905 describes the preparation of a printing
plate by ink-jetting an alcohol-soluble resin in an
organic solvent onto an aluminum printing plate.

JP-A-56105960 describes the formation of a printing
35 plate by ink-jetting onto a support e.g. an anodised

PRINTING PLATES AND A METHOD FOR THEIR PREPARATION.**Field of the Invention**

This invention relates to novel printing plates, to a
5 method for their preparation and to a lithographic
printing process employing the plates.

Background of the Invention

Printing plates suitable for offset lithographic
printing are known which comprise a support having
10 non-image areas which are hydrophilic and image areas
which are hydrophobic and ink-receptive.

The art of lithographic printing is based upon the
immiscibility of oil and water, wherein the oily
material or ink is preferentially retained by the
15 image area and water or fountain solution is
preferentially retained by the non-image area. When a
suitably prepared surface is moistened with water and
an ink is then applied the background or non-image
area retains the water and repels the ink while the
20 image area accepts the ink and repels the water. The
ink on the image area is then transferred to the
surface of a material upon which the image is to be
reproduced, such as paper, cloth and the like.

Commonly the ink is transferred to an intermediate
25 material called the blanket which in turn transfers
the ink to the surface of the material upon which the
image is to be reproduced.

Ink-jetting is the non-impact method for producing
images by the deposition of ink droplets on a
30 substrate in response to digital signals.

JP-A-53015905 describes the preparation of a printing
plate by ink-jetting an alcohol-soluble resin in an
organic solvent onto an aluminum printing plate.

JP-A-56105960 describes the formation of a printing
35 plate by ink-jetting onto a support e.g. an anodised

aluminum plate an ink capable of forming an oleophilic image and containing a hardening substance such as epoxy-soybean oil together with benzoyl peroxide or a photo-hardening substance such as an unsaturated polyester.

5 European Patent Application No. 882584 describes a method of preparing a printing plate comprising producing an oleophilic image on the surface of a support by ink-jet printing the image on the surface using an aqueous solution or of a salt of a hydrophobic organic acid e.g. oleic acid.

10 G.B. Patent Application No. 2,332,646 describes a method of preparing a printing plate comprising producing an oleophilic image on the surface of a support by ink-jet printing the image on the surface using an aqueous solution or aqueous colloidal dispersion of a polymer bearing water-solubilising groups wherein the water solubilising groups interact with the surface of the support thereby binding the polymer to the support and rendering the polymer insoluble.

15 20

Problem to be solved by the Invention

The prior art methods involve the use of organic solvents or photo-hardenable compounds or polymers which introduces some risk that the inlets may become blocked by the polymer.

A solution to these problems has now been invented in which an oligomer having hydrophilic and hydrophobic groups in the molecule, is used as an aqueous dispersion to prepare the image on the printing plate.

25 30

Summary of the Invention

According to the present invention a method for the preparation of a lithographic printing plate comprises

35

aluminum plate an ink capable of forming an oleophilic image and containing a hardening substance such as epoxy-soybean oil together with benzoyl peroxide or a photo-hardening substance such as an unsaturated polyester.

European Patent Application No. 882584 describes a method of preparing a printing plate comprising producing an oleophilic image on the surface of a support by ink-jet printing the image on the surface using an aqueous solution or of a salt of a hydrophobic organic acid e.g. oleic acid.

G.B. Patent Application No. 2,332,646 describes a method of preparing a printing plate comprising producing an oleophilic image on the surface of a support by ink-jet printing the image on the surface using an aqueous solution or aqueous colloidal dispersion of a polymer bearing water-solubilising groups wherein the water solubilising groups interact with the surface of the support thereby binding the polymer to the support and rendering the polymer insoluble.

Problem to be solved by the Invention

The prior art methods involve the use of organic solvents or photo-hardenable compounds or polymers which introduces some risk that the inlets may become blocked by the polymer.

A solution to these problems has now been invented in which an oligomer having hydrophilic and hydrophobic groups in the molecule, is used as an aqueous dispersion to prepare the image on the printing plate.

Summary of the Invention

According to the present invention a method for the preparation of a lithographic printing plate comprises

forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both
5 hydrophilic and hydrophobic groups.

Advantageous Effect of the Invention

The method of the invention offers a rapid, simple and direct way to make a printing plate from digital data
10 using relatively low cost equipment and without light sensitive materials.

Compared with the methods disclosed in the prior art, the method of the invention requires no processing of the plate and uses dilute aqueous dispersions having a
15 low level of environmental impact and low health risk. In addition the risk of the jets being blocked by polymer is reduced.

Brief Description of the Drawings

20 The drawing is a sketch showing the formation of a printing plate by ink-jetting.

Detailed Description of the Invention

The oligomer may be applied as an aqueous solution or
25 an aqueous emulsion.

The term aqueous is intended to include the optional presence of organic liquids such as those that are miscible with water e.g. polyhydric alcohols e.g. ethylene glycol, diethylene glycol, trimethylene
30 glycol or trimethylol propane.

The proportion of water in the aqueous liquid in which the oligomer is dissolved or dispersed is at least 40%, preferably at least 75%, more preferably at least 80% by weight.

forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both
5 hydrophilic and hydrophobic groups.

Advantageous Effect of the Invention

The method of the invention offers a rapid, simple and direct way to make a printing plate from digital data
10 using relatively low cost equipment and without light sensitive materials.

Compared with the methods disclosed in the prior art, the method of the invention requires no processing of the plate and uses dilute aqueous dispersions having a
15 low level of environmental impact and low health risk. In addition the risk of the jets being blocked by polymer is reduced.

Brief Description of the Drawings

20 The drawing is a sketch showing the formation of a printing plate by ink-jetting.

Detailed Description of the Invention

The oligomer may be applied as an aqueous solution or
25 an aqueous emulsion.

The term aqueous is intended to include the optional presence of organic liquids such as those that are miscible with water e.g. polyhydric alcohols e.g. ethylene glycol, diethylene glycol, trimethylene
30 glycol or trimethylol propane.

The proportion of water in the aqueous liquid in which the oligomer is dissolved or dispersed is at least 40%, preferably at least 75%, more preferably at least 80% by weight.

The oligomer preferably comprises from 2 to 10 repeating units more preferably 3 to 5 and preferably the number of hydrophilic groups in the oligomer is also from 2 to 10.

- 5 Because the oligomer contains both hydrophobic and hydrophilic it will have the characteristics of a surfactant.

- The hydrophilic groups, which may be anionic, serve to bind the oligomer to the hydrophilic surface thereby rendering the oligomer insoluble.
- 10 The hydrophobic portion of the molecule.
- The hydrophilic groups may be acid groups such as carboxylic, sulphononic, sulphate, phosphate or phosphonic acids. Some or all of such acid groups may exist as salts for example those of an alkali metal or ammonium.

- The molecular weight of the oligomers is typically in the range from about 500 to about 5000, preferably from about 1000 to about 3000.
- 20 The support may be any support suitable for printing plates. Typical supports include metallic and polymeric sheets or foils. The surface of the support may be treated or coated to provide the necessary interaction with the oligomer. Examples of surface coatings include a metallic oxide and gelatin.

- 25 Preferably a support having a metallic surface is used. Preferably the metallic surface is oxidized.
- 30 In a particularly preferred embodiment of the invention a support having an anodized aluminum surface is employed.
- 35 Jet velocity, separation length of the droplets, drop size and stream stability are greatly affected by the surface tension and the viscosity of the aqueous

The oligomer preferably comprises from 2 to 10 repeating units more preferably 3 to 5 and preferably the number of hydrophilic groups in the oligomer is also from 2 to 10.

- 5 Because the oligomer contains both hydrophobic and hydrophilic it will have the characteristics of a surfactant.

The hydrophilic groups, which may be anionic, serve to bind the oligomer to the hydrophilic surface thereby
10 rendering the oligomer insoluble.

The hydrophobic group may comprise a non polar hydrocarbon portion of the molecule.

The hydrophilic groups may be acid groups such as carboxylic, sulphonic, sulphate, phosphate or
15 phosphonic acids. Some or all of such acid groups may exist as salts for example those of an alkali metal or ammonium.

The molecular weight of the oligomers is typically in the range from about 500 to about 5000, preferably
20 from about 1000 to about 3000.

The support may be any support suitable for printing plates. Typical supports include metallic and polymeric sheets or foils. The surface of the support may be treated or coated to provide the necessary
25 interaction with the oligomer. Examples of surface coatings include a metallic oxide and gelatin coatings.

Preferably a support having a metallic surface is used. Preferably the metallic surface is oxidized.
30 In a particularly preferred embodiment of the invention a support having an anodized aluminum surface is employed.

Jet velocity, separation length of the droplets, drop size and stream stability are greatly affected by the
35 surface tension and the viscosity of the aqueous

composition. Ink-jet inks suitable for use with ink-jet printing systems may have a surface tension in the range from 20 to 60, preferably 30 to 50 dynes/cm. Control of the surface tension in aqueous inks may be accomplished by addition of small amounts of surfactants. The level of surfactants to be used can be determined through simple trial and error experiments. Anionic and non-ionic surfactants may be selected from those disclosed in US Patents Nos. 5,324,349; 4,156,616; and 5,279,654 as well as many other surfactants known in the ink-jet art. Commercial surfactants include the Surfynol (Trade Mark) range from Air Products; the Zonyl (Trade Mark) range from DuPont; the Fluorad (Trade Mark) range from 3M and the Aerosol (Trade Mark) range from Cyanamid. The viscosity of the ink is preferably no greater than 20 centipoise e.g. from 1 to 10, preferably from 1 to 5 centipoise at 20°C.

The emulsion used in the ink-jet printer may comprise other ingredients, for example water-soluble liquids or solids with a substantially higher boiling point than water, e.g. ethanediol, as well as other types of oleophilic precursors such as the sodium salt of oleic acid. A humectant or co-solvent may be included to help prevent the ink from drying out or crusting in the orifices of the print head. A penetrant may also optionally be included to help the ink penetrate the surface of the support. A biocide, such as Proxel (Trade Mark) GXL from Zeneca Colours may be added to prevent microbial growth which may otherwise occur in the ink over time.

The aqueous emulsion is employed in ink-jet printing wherein drops of the emulsion are applied in a controlled fashion to the surface of the support by

composition. Ink-jet inks suitable for use with ink-jet printing systems may have a surface tension in the range from 20 to 60, preferably 30 to 50 dynes/cm. Control of the surface tension in aqueous inks may be accomplished by addition of small amounts of surfactants. The level of surfactants to be used can be determined through simple trial and error experiments. Anionic and non-ionic surfactants may be selected from those disclosed in US Patents Nos. 5,324,349; 4,156,616; and 5,279,654 as well as many other surfactants known in the ink-jet art. Commercial surfactants include the Surfynol (Trade Mark) range from Air Products; the Zonyl (Trade Mark) range from DuPont; the Fluorad (Trade Mark) range from 3M and the Aerosol (Trade Mark) range from Cyanamid. The viscosity of the ink is preferably no greater than 20 centipoise e.g. from 1 to 10, preferably from 1 to 5 centipoise at 20°C.

The emulsion used in the ink-jet printer may comprise other ingredients, for example water-soluble liquids or solids with a substantially higher boiling point than water, e.g. ethanediol, as well as other types of oleophilic precursors such as the sodium salt of oleic acid. A humectant or co-solvent may be included to help prevent the ink from drying out or crusting in the orifices of the print head. A penetrant may also optionally be included to help the ink penetrate the surface of the support. A biocide, such as Proxel (Trade Mark) GXL from Zeneca Colours may be added to prevent microbial growth which may otherwise occur in the ink over time.

The aqueous emulsion is employed in ink-jet printing wherein drops of the emulsion are applied in a controlled fashion to the surface of the support by

ejecting droplets from a plurality of nozzles or orifices in a print head of an ink-jet printer. Commercially available ink-jet printers use several different schemes to control the deposition of the ink droplets. Such schemes are generally of two types: continuous stream or drop-on-demand.

In drop-on-demand systems a droplet of ink is ejected from an orifice directly to a position on the ink receptive layer by pressure created by, for example, a piezoelectric device, an acoustic device, or a thermal process controlled in accordance with digital signals. An ink droplet is not generated and ejected through the orifice of the print head unless it is needed. Ink-jet printing methods and related printers are commercially available and need not be described in detail.

The aqueous emulsion may have properties compatible with a wide range of ejecting conditions, e.g. driving voltages, and pulse widths for thermal ink-jet printers, driving frequencies of the piezoelectric element for either a drop-on-demand device or continuous device and the shape and size of the nozzle.

The support for the lithographic printing plate is typically formed of aluminum which has been grained for example by electrochemical graining and then anodized for example by means of anodizing techniques employing sulfuric acid and/or phosphoric acid. Methods of both graining and anodizing are well known in the art.

After writing the image to the printing plate, the printing plate may be inked with printing inking the normal way and the plate used on a printing press. Before inking the plate may be treated with an aqueous solution of natural gum, such as gum acacia or of a

ejecting droplets from a plurality of nozzles or orifices in a print head of an ink-jet printer. Commercially available ink-jet printers use several different schemes to control the deposition of the ink droplets. Such schemes are generally of two types: continuous stream or drop-on-demand.

In drop-on-demand systems a droplet of ink is ejected from an orifice directly to a position on the ink receptive layer by pressure created by, for example, a piezoelectric device, an acoustic device, or a thermal process controlled in accordance with digital signals. An ink droplet is not generated and ejected through the orifice of the print head unless it is needed. Ink-jet printing methods and related printers are commercially available and need not be described in detail.

The aqueous emulsion may have properties compatible with a wide range of ejecting conditions, e.g. driving voltages, and pulse widths for thermal ink-jet printers, driving frequencies of the piezoelectric element for either a drop-on-demand device or continuous device and the shape and size of the nozzle.

The support for the lithographic printing plate is typically formed of aluminum which has been grained for example by electrochemical graining and then anodized for example by means of anodizing techniques employing sulfuric acid and/or phosphoric acid. Methods of both graining and anodizing are well known in the art.

After writing the image to the printing plate, the printing plate may be inked with printing inking the normal way and the plate used on a printing press. Before inking the plate may be treated with an aqueous solution of natural gum, such as gum acacia or of a

synthetic gum such as carboxymethylcellulose, as is known in the art of printing see for example Chapter 10 of "The Lithographer's Manual" edited by Charles Shapiro and published by The Graphic Arts Technical Foundation, Inc. Pittsburgh, Pennsylvania (1966). Referring to the drawing: from an ink-jet printer head 2 droplets of dispersion (solution or emulsion) are jetted onto a hydrophilic surface 6 of a printing plate 8. The direction of movement of the printing head is indicated by the arrow. A hydrophobic image 10 is produced on the support.

The invention is illustrated by the following Examples.

Preparation 1.

Preparation of tetradecylthio'tri(acrylamidoglycolic acid).

The monomer (acrylamidoglycolic acid) (16.3g, 100mmol) was dissolved in methanol (200ml) and purged with nitrogen gas for 15 minutes. The mixture was heated to 62.5°C and a solution of tetradecylmercaptan (7.68g, 33.3mmol) and AIBN (0.24g) in methanol (50ml) which had also been purged with nitrogen gas, was added in one portion. The mixture was refluxed under an atmosphere of nitrogen gas for 3 hours. The cooled reaction mixture was washed with heptane (2 X 150ml) and solvent removed by evaporation at reduced pressure to give 16.92g of the water-soluble product with an average of 3 monomer units attached to the thiol.

Example 1

A 1 wt% solution in water of the oligomeric surfactant prepared in Preparation 1 above was painted onto a piece of Kodak anodised aluminum printing plate using an artist's paintbrush to make an image. The image was allowed to dry naturally and then the plate was wetted with a 0.05wt% solution of "Viscofas", a proprietary

synthetic gum such as carboxymethylcellulose, as is known in the art of printing see for example Chapter 10 of "The Lithographer's Manual" edited by Charles Shapiro and published by The Graphic Arts Technical Foundation, Inc. Pittsburgh, Pennsylvania (1966).
5 Referring to the drawing: from an ink-jet printer head 2 droplets of dispersion (solution or emulsion) are jetted onto a hydrophilic surface 6 of a printing plate 8. The direction of movement of the printing
10 head is indicated by the arrow. A hydrophobic image 10 is produced on the support.

The invention is illustrated by the following Examples.

Preparation 1.

15 Preparation of tetradecylthio'tri(acrylamidoglycolic acid).

The monomer (acrylamidoglycolic acid) (16.3g, 100mmol) was dissolved in methanol (200ml) and purged with nitrogen gas for 15 minutes. The mixture was heated
20 to 62.5°C and a solution of tetradecylmercaptan (7.68g, 33.3mmol) and AIBN (0.24g) in methanol (50ml) which had also been purged with nitrogen gas, was added in one portion. The mixture was refluxed under an atmosphere of nitrogen gas for 3 hours. The cooled
25 reaction mixture was washed with heptane (2 X 150ml) and solvent removed by evaporation at reduced pressure to give 16.92g of the water-soluble product with an average of 3 monomer units attached to the thiol.

Example 1

30 A 1 wt% solution in water of the oligomeric surfactant prepared in Preparation 1 above was painted onto a piece of Kodak anodised aluminum printing plate using an artist's paintbrush to make an image. The image was allowed to dry naturally and then the plate was wetted
35 with a 0.05wt% solution of "Viscofas", a proprietary

lithographic fountain preparation, using cotton wool. The plate was then lightly rubbed with a small amount of printers ink (BASF Fishburns Minilith Black) on a piece of cotton wool. The image that had been painted
5 on selectively took up the ink, showing a good representation of the painted image with minimal image degradation. The inked image was resistant to firm rubbing.

10 **Example 2.**

In a similar manner, the image was painted onto a polyester printing plate with a hydrophilic layer containing silica (Autotype Omega E-Z). Again selective inking of the painted area was seen with
15 good quality image.

Preparation 2.

Neutralisation of
20 tetradecylthio'tri'(acrylamidoglycolic acid): the trisodium salt of the oligomeric surfactant was prepared by dissolving the above product in water at a concentration of 1 wt% and titrating with aqueous sodium hydroxide using electrochemical detection of
25 the end-point.

Example 3.

In a similar manner a 1 wt% solution in water of the
30 sodium salt of Preparation 2 also showed selective inking of a painted image on a Kodak (Registered Trade Mark) anodised aluminum printing plate.

Preparation 3.

35

lithographic fountain preparation, using cotton wool. The plate was then lightly rubbed with a small amount of printers ink (BASF Fishburns Minilith Black) on a piece of cotton wool. The image that had been painted
5 on selectively took up the ink, showing a good representation of the painted image with minimal image degradation. The inked image was resistant to firm rubbing.

10 **Example 2.**

In a similar manner, the image was painted onto a polyester printing plate with a hydrophilic layer containing silica (Autotype Omega E-Z). Again selective inking of the painted area was seen with
15 good quality image.

Preparation 2.

Neutralisation of
20 tetradecylthio'tri'(acrylamidoglycolic acid): the trisodium salt of the oligomeric surfactant was prepared by dissolving the above product in water at a concentration of 1 wt% and titrating with aqueous sodium hydroxide using electrochemical detection of
25 the end-point.

Example 3.

In a similar manner a 1 wt% solution in water of the
30 sodium salt of Preparation 2 also showed selective inking of a painted image on a Kodak (Registered Trade Mark) anodised aluminum printing plate.

Preparation 3.

35

Preparation of octadecylthio'tetra'(2-acrylamido-2-methyl-1-propanesulphonic acid): octadecanethiol (28.66g, 0.10mol) and 2-acrylamido-2-methyl-1-propane sulfonic acid (82.9g, 0.40mol) were stirred together
5 with azobisisobutyronitrile (AIBN) (1.0g) in methanol (500ml). The mixture was degassed with argon then refluxed under an argon atmosphere for 18 hours. The reaction mixture still appeared a little cloudy. On cooling a white solid began to form. The mixture was
10 reheated on a steam bath which caused oily globules to appear. The hot solution was filtered under suction on a sinter, trapping the oily globules as a white rubbery solid which failed to dissolve in water, sodium hydroxide or ethyl acetate. The remaining
15 solution on cooling gave another white semicrystalline solid which was filtered off. The remaining solution was washed with heptane (500ml) and the methanol evaporated to give the product as a white solid (92.4g).

20 **Example 4.**

In a similar manner a 1 wt% solution in water of the oligomeric product from Preparation 3 also showed selective inking with good quality image resistant to rubbing.

25

Preparation 4

Preparation of octadecathio'tetra'(2-acrylamido-2-methyl-1-propanesulphonic acid sodium salt).
Based on titration results the product from Example 3
30 (50.00g, 0.0448 mol) was suspended in water (100ml) in a round bottom flask and stirred at room temperature. Sodium hydroxide solution (10M, 18.60ml) was added and the solution warmed to 45°C for about 15 minutes then allowed to cool while stirring continued (total time
35 0.5 hours). The resulting pale yellow solution was

Preparation of octadecylthio'tetra'(2-acrylamido-2-methyl-1-propanesulphonic acid): octadecanethiol (28.66g, 0.10mol) and 2-acrylamido-2-methyl-1-propane sulfonic acid (82.9g, 0.40mol) were stirred together
5 with azobisisobutyronitrile (AIBN) (1.0g) in methanol (500ml). The mixture was degassed with argon then refluxed under an argon atmosphere for 18 hours. The reaction mixture still appeared a little cloudy. On cooling a white solid began to form. The mixture was
10 reheated on a steam bath which caused oily globules to appear. The hot solution was filtered under suction on a sinter, trapping the oily globules as a white rubbery solid which failed to dissolve in water, sodium hydroxide or ethyl acetate. The remaining
15 solution on cooling gave another white semicrystalline solid which was filtered off. The remaining solution was washed with heptane (500ml) and the methanol evaporated to give the product as a white solid (92.4g).

20 **Example 4.**

In a similar manner a 1 wt% solution in water of the oligomeric product from Preparation 3 also showed selective inking with good quality image resistant to rubbing.

25

Preparation 4

Preparation of octadecathio'tetra'(2-acrylamido-2-methyl-1-propanesulphonic acid sodium salt).
Based on titration results the product from Example 3
30 (50.00g, 0.0448 mol) was suspended in water (100ml) in a round bottom flask and stirred at room temperature. Sodium hydroxide solution (10M, 18.60ml) was added and the solution warmed to 45°C for about 15 minutes then allowed to cool while stirring continued (total time
35 0.5 hours). The resulting pale yellow solution was

freeze dried to give the product as a white solid (50.1g).

Example 5.

In a similar manner a 1 wt% solution of the oligomeric
5 surfactant from Preparation 4 showed similar behaviour.

Preparation 5.

Preparation of Tyloxapol disulphate disodium salt.

10 Tyloxapol is a novolak resin comprising an ethoxylated phenol formaldehyde resin.

Tyloxapol (5g, about 1.3mmol) was dissolved in 1,2-dichloroethane (100ml) and chlorosulphonic acid (0.3g, 2.6mmol) was added and the mixture heated at 50°C for
15 2.5 hours with exclusion of moisture. The mixture was then cooled and solvent evaporated under reduced pressure. Water (100ml) was added and stirred to dissolve. The pH was adjusted to 10 to 11 with aqueous sodium hydroxide and evaporated to dryness on a steam bath.
20 The residue was treated with methanol and the inorganic salts filtered off. The product was isolated by evaporation under reduced pressure and dried under high vacuum.

25 **Example 6.**

The oligomer of Preparation 2 was formulated according to the table to give 20ml of solution which was placed in an empty clean ink-jet cartridge.

30

freeze dried to give the product as a white solid (50.1g).

Example 5.

In a similar manner a 1 wt% solution of the oligomeric
5 surfactant from Preparation 4 showed similar behaviour.

Preparation 5.

Preparation of Tyloxapol disulphate disodium salt.

10 Tyloxapol is a novolak resin comprising an ethoxylated phenol formaldehyde resin.

Tyloxapol (5g, about 1.3mmol) was dissolved in 1,2-dichloroethane (100ml) and chlorosulphonic acid (0.3g, 2.6mmol) was added and the mixture heated at 50°C for
15 2.5 hours with exclusion of moisture. The mixture was then cooled and solvent evaporated under reduced pressure. Water (100ml) was added and stirred to dissolve. The pH was adjusted to 10 to 11 with aqueous sodium hydroxide and evaporated to dryness on a steam bath.
20 The residue was treated with methanol and the inorganic salts filtered off. The product was isolated by evaporation under reduced pressure and dried under high vacuum.

25 **Example 6.**

The oligomer of Preparation 2 was formulated according to the table to give 20ml of solution which was placed in an empty clean ink-jet cartridge.

30

component	stock solutions (wt%)	vol used in ink (ml)
oligomer	1	9.6
ethanedio 1	15	1.4
sorbitol	5	1.0
water		8.0
total		20.0

A standard test-object image was printed onto an Autotype Omega E-Z polyester printing plate using an Epson 200 ink-jet printer, the image allowed to dry and the plate then placed on a printing press (Heidelberg T-Offset) and run using Varn PressMaster Universal Fountain Solution (diluted 1 plus 15) and Van Son Rubber Based Ink-VS310 "Pantone" Black to give clear prints of the test image after rapid ink-up.

Example 7.

A 0.5% weight aqueous solution of the product of preparation 5 was prepared and the procedure of Example 2 repeated. Again selective inking of the painted area was seen with good quality image.

component	stock solutions (wt%)	vol used in ink (ml)
oligomer	1	9.6
ethanedio 1	15	1.4
sorbitol	5	1.0
water		8.0
total		20.0

A standard test-object image was printed onto an Autotype Omega E-Z polyester printing plate using an Epson 200 ink-jet printer, the image allowed to dry and the plate then placed on a printing press (Heidelberg T-Offset) and run using Varn PressMaster Universal Fountain Solution (diluted 1 plus 15) and Van Son Rubber Based Ink-VS310 "Pantone" Black to give clear prints of the test image after rapid ink-up.

Example 7.

A 0.5% weight aqueous solution of the product of preparation 5 was prepared and the procedure of Example 2 repeated. Again selective inking of the painted area was seen with good quality image.

CLAIMS:

1. A method for the preparation of a lithographic printing plate which method comprises
5 forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both hydrophilic and hydrophobic groups.
10
2. A method as claimed in claim 1 wherein the number of hydrophilic groups in the oligomer is from 2 to 10.
3. A method as claimed in claim 1 or 2 wherein the
15 molecular weight of the oligomer is from 500 to 5000.
4. A method as claimed in any one of the preceding claims wherein at least one of the hydrophilic groups is an acid group which has been neutralized.
20
5. A method as claimed in any one of the preceding claims wherein the hydrophilic groups are selected from carboxylic, sulphonic or phosphonic acids and the salts thereof.
25
6. A printing plate comprising a hydrophilic support having deposited thereon an image comprising an oligomer containing in the molecule hydrophobic and hydrophilic groups wherein the latter serve to bind it
30 to the support.
7. A printing plate as claimed in claim 6 wherein the oligomer has been ink-jetted onto the plate in the form of an aqueous dispersion.
35

CLAIMS:

1. A method for the preparation of a lithographic printing plate which method comprises
5 forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both hydrophilic and hydrophobic groups.
10
2. A method as claimed in claim 1 wherein the number of hydrophilic groups in the oligomer is from 2 to 10.
3. A method as claimed in claim 1 or 2 wherein the
15 molecular weight of the oligomer is from 500 to 5000.
4. A method as claimed in any one of the preceding claims wherein at least one of the hydrophilic groups is an acid group which has been neutralized.
20
5. A method as claimed in any one of the preceding claims wherein the hydrophilic groups are selected from carboxylic, sulphonic or phosphonic acids and the salts thereof.
25
6. A printing plate comprising a hydrophilic support having deposited thereon an image comprising an oligomer containing in the molecule hydrophobic and hydrophilic groups wherein the latter serve to bind it
30 to the support.
7. A printing plate as claimed in claim 6 wherein the oligomer has been ink-jetted onto the plate in the form of an aqueous dispersion.
35


8. A printing process which comprises employing a printing plate which has been prepared by a method as claimed in any one of claims 1 to 5.

5


8. A printing process which comprises employing a printing plate which has been prepared by a method as claimed in any one of claims 1 to 5.

5

1/1



1/1



PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B41C 1/10	A3	(11) International Publication Number: WO 00/37261 (43) International Publication Date: 29 June 2000 (29.06.00)
(21) International Application Number: PCT/GB99/04238 (22) International Filing Date: 14 December 1999 (14.12.99) (30) Priority Data: 9828154.6 22 December 1998 (22.12.98) GB (71) Applicant (for all designated States except US): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): NEWINGTON, Ian, Martin [GB/GB]; 11 Ashtree Walk, Hazlemere, High Wycombe, Bucks HP15 7TG (GB). WEAR, Trevor, John [GB/GB]; 22 Balmoral Road, South Harrow, Middlesex HA2 8TD (GB). (74) Agent: NUNNEY, R., F., A.; Kodak Limited, Headstone Drive, Harrow, Middlesex HA1 4TY (GB).	(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> (88) Date of publication of the international search report: 14 September 2000 (14.09.00)	
(54) Title: PRINTING PLATES AND A METHOD FOR THEIR PREPARATION (57) Abstract A method for the preparation of a lithographic printing plate comprises forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both hydrophilic and hydrophobic groups. The number of repeating units in the oligomer may be from 2 to 10 and the number of hydrophilic groups in the oligomer may also be from 2 to 10. Preferably the molecular weight of the oligomer is from about 500 to about 5000.		

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁷ : B41C 1/10	A3	(11) International Publication Number: WO 00/37261 (43) International Publication Date: 29 June 2000 (29.06.00)
(21) International Application Number: PCT/GB99/04238 (22) International Filing Date: 14 December 1999 (14.12.99) (30) Priority Data: 9828154.6 22 December 1998 (22.12.98) GB (71) Applicant (for all designated States except US): EASTMAN KODAK COMPANY [US/US]; 343 State Street, Rochester, NY 14650 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): NEWINGTON, Ian, Martin [GB/GB]; 11 Ashtree Walk, Hazlemere, High Wycombe, Bucks HP15 7TG (GB). WEAR, Trevor, John [GB/GB]; 22 Balmoral Road, South Harrow, Middlesex HA2 8TD (GB). (74) Agent: NUNNEY, R., F., A.; Kodak Limited, Headstone Drive, Harrow, Middlesex HA1 4TY (GB).		(81) Designated States: JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> (88) Date of publication of the international search report: 14 September 2000 (14.09.00)
(54) Title: PRINTING PLATES AND A METHOD FOR THEIR PREPARATION (57) Abstract A method for the preparation of a lithographic printing plate comprises forming an oleophilic image on the surface of a hydrophilic support by depositing, preferably by ink-jetting, the image on the surface using an aqueous dispersion of an oligomer having in the molecule both hydrophilic and hydrophobic groups. The number of repeating units in the oligomer may be from 2 to 10 and the number of hydrophilic groups in the oligomer may also be from 2 to 10. Preferably the molecular weight of the oligomer is from about 500 to about 5000.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/04238

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B41C1/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B41C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 213 041 A (KANCK ASBJORN J) 25 May 1993 (1993-05-25) column 2, line 1 - line 18 examples	1-8
A	US 4 869 934 A (JETHWA ANIL P) 26 September 1989 (1989-09-26) example B, footnote b	1,6,8
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 07, 31 July 1996 (1996-07-31) & JP 08 069108 A (NEW OJI PAPER CO LTD), 12 March 1996 (1996-03-12) abstract	1,6,8
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 June 2000

Date of mailing of the international search report

21/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Markham, R

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/04238

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B41C1/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B41C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 213 041 A (KANCK ASBJORN J) 25 May 1993 (1993-05-25) column 2, line 1 - line 18 examples	1-8
A	US 4 869 934 A (JETHWA ANIL P) 26 September 1989 (1989-09-26) example B, footnote b	1,6,8
A	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 07, 31 July 1996 (1996-07-31) & JP 08 069108 A (NEW OJI PAPER CO LTD), 12 March 1996 (1996-03-12) abstract	1,6,8
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 June 2000

Date of mailing of the international search report

21/06/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Markham, R

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 99/04238

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 882 584 A (EASTMAN KODAK CO) 9 December 1998 (1998-12-09) cited in the application the whole document ---	1,6,8
A	EP 0 616 017 A (CANON KK) 21 September 1994 (1994-09-21) page 4, line 1 -page 12, line 41 examples -----	1

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/04238

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 882 584 A (EASTMAN KODAK CO) 9 December 1998 (1998-12-09) cited in the application the whole document ---	1,6,8
A	EP 0 616 017 A (CANON KK) 21 September 1994 (1994-09-21) page 4, line 1 -page 12, line 41 examples -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/04238

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5213041 A	25-05-1993	DE 59205729 D EP 0520332 A JP 5185575 A	25-04-1996 30-12-1992 27-07-1993
US 4869934 A	26-09-1989	AU 614655 B AU 3947089 A DK 424289 A EP 0358984 A NO 893459 A	05-09-1991 22-03-1990 17-03-1990 21-03-1990 19-03-1990
JP 08069108 A	12-03-1996	NONE	
EP 0882584 A	09-12-1998	JP 11070632 A	16-03-1999
EP 0616017 A	21-09-1994	JP 6264017 A JP 6279718 A AT 183537 T DE 69420065 D DE 69420065 T US 5696182 A	20-09-1994 04-10-1994 15-09-1999 23-09-1999 20-04-2000 09-12-1997

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/04238

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5213041 A	25-05-1993	DE 59205729 D EP 0520332 A JP 5185575 A	25-04-1996 30-12-1992 27-07-1993
US 4869934 A	26-09-1989	AU 614655 B AU 3947089 A DK 424289 A EP 0358984 A NO 893459 A	05-09-1991 22-03-1990 17-03-1990 21-03-1990 19-03-1990
JP 08069108 A	12-03-1996	NONE	
EP 0882584 A	09-12-1998	JP 11070632 A	16-03-1999
EP 0616017 A	21-09-1994	JP 6264017 A JP 6279718 A AT 183537 T DE 69420065 D DE 69420065 T US 5696182 A	20-09-1994 04-10-1994 15-09-1999 23-09-1999 20-04-2000 09-12-1997

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 56-105960

(43)Date of publication of application : 22.08.1981

(51)Int.Cl.

B41C 1/10

(21)Application number : 55-007645

(71)Applicant : FUJI PHOTO FILM CO LTD

(22)Date of filing : 25.01.1980

(72)Inventor : NAKAYAMA TAKAO
OHASHI AZUSA

(54) PREPARATION OF OFFSET PRINTING PLATE

(57)Abstract:

PURPOSE: To obtain an offset printing plate readily without the necessity of preliminary and complicated developing processes by a method wherein a picture is prepared with such ink as is able to form a lipophilic picture on a hydrophilic surface and the ink is hardened.

CONSTITUTION: A picture is prepared by the ink-jet method with the use of ink capable of forming a lipophilic picture on a hydrophilic surface preferably having a microporous aluminum oxide layer, whereas the ink is preferably a hardenable ink containing no solvent, but containing a coloring substance and a hardening accelerator. The ink use to form the picture by an ink-injection process is hardened to obtain an offset printing plate as intended.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

